

## **PRODUCT HEALTH & SAFETY**

## PIR INSULATION RIGID POLYISOCYANURATE

#### **SECTION 1: PRODUCT & COMPANY IDENTIFICATION**

#### PRODUCT NAME: SYNONYMS: PRODUCT CODES:

**MANUFACTURER:** 

PHONE:

FAX:

EMAIL:

WEBSITE:

PIR Insulation

### PIR

- **THIN-R**XT/CW Partial Fill Cavity Wall
- XT/CWP Partial Fill Cavity Wall
  XT/CWP Partial Fill Cavity Plus
- XT/TL Thermal Liner (Dot & Dab
- XT/TL/MF Thermal Liner (Mech Fix
- XT/TF Timber Frame
- XT/UF Underfloor
- XT/HYF Hyfloor
- XT/SK Sarking
- XT/WALK-R
- XT/PR Pitched Roof
- AT/PR PILCHED ROOT
- XT/GA General Application
- FR/ALU Flat Roof
- FR/MG Flat Roof
- FR/BGM Flat Roof
- FR/TP Thermal Ply
- TR/MG Tapered Roof
- TR/BGM Tapered Roof
- TR/ALU Tapered Roof

#### Unilin Insulation UK Ltd Park Road, Holmewood, Chesterfield, Derbyshire, UK, S42 5UY

+44 (0)371 222 1033 +44 (0)371 222 1044 info.ui@unilin.com www.unilininsulation.co.uk

#### **SECTION 2: HAZARDS IDENTIFICATION**

No identified hazards

#### **SECTION 3: PRODUCT COMPOSITION**

CORE:	Rigid thermoset urethane insulation (PIR) ref EN 13165	
PRODUCT FACINGS:	Laminate of foil/paper Kraft paper Mineral coated glass Bitumen coated glass	WBP exterior grade plywood Gypsum plasterboard Resistant Magnesium Silicate

#### XTROLINER

- XtroWall
- XO/UF Floor: Solid & Suspended XO/FB Framing Board
- XO/SK Sarking
- XO/STP Soffit Plus
- XO/PR Pitched Roof

#### CAVITYTHERM

• CT/PIR Cavity Therm

#### XTRAFALL

- XF/ALU
- XF/MG
- XF/BGM

# **BUNILIN** INSULATION

### **PRODUCT HEALTH & SAFETY**

SECTION 4: FIRST AID MEASURES		
INHALATION: EYES:	Dust is non-hazardous. If dust is inhaled, person should get some fresh air. Dust should be removed by flushing with water.	
SKIN:	Non-sensitizing. When MG & BG are handled, some skin irritation may occur due to glass fibres. Ensure good hygiene is followed, after handling ensure skin is washed using soap/proprietary cleanser.	
INGESTION:	No information available.	
OTHER:	Seek medical attention if discomfort persists.	

#### **SECTION 5: FIRE-FIGHTING MEASURES**

EXTINGUISHING MEDIA:	Water-Spray (Fog), Foam, CO <sub>2</sub> , Dry Power
FIRE & EXPLOSION HAZARDS:	None Identified. Fire fighters should use SCBA gear. Burning foam should be saturated with water. Dust classification St Class 1 (weak explosion potential).

#### **SECTION 6: ACCIDENTAL RELEASE MEASURES**

Not Applicable

#### **SECTION 7: HANDLING & STORAGE**

Products should be stored off the ground, on a clean, flat surface and under cover. Products should be stored in a location free from ignition hazards and direct radiant heat. The polythene wrapping is not considered adequate protection for outdoor storage. It is recommended that suitable PPE to be used in the handling and cutting of these materials. To reduce dust it is recommended to use a trimming knife rather than a saw when cutting boards.

#### **SECTION 8: EXPOSURE CONTROLS / PERSONAL PROTECTION**

RESPIRATORY PROTECTION:	Dust is non-hazardous. Dust from plasterboard / plywood facings may cause respiratory irritation. It is recommended that a dust mask is worn when cutting. In confined areas it is recommended that extraction is used when mechanical cutting is being performed.
HANDS:	It is recommended that gloves are worn when handling product.
EYE PROTECTION:	Eye protection is recommended during mechanical cutting. In bright sunlight, it is recommended to wear UV glasses when installing ALU/MG products.



### **PRODUCT HEALTH & SAFETY**

#### SECTION 8 (CONTINUED): EXPOSURE CONTROLS / PERSONAL PROTECTION

SKIN PROTECTION:	Non- sensitizing. To reduce the risk of cut hazard from edges of board it is advisable to wear general purpose gloves. In bright sunlight it is recommended to wear UV skin protection when installing ALU/MG product.
OTHER:	This product is non-load bearing. The facings on ALU faced products can be slippy underfoot when wet.

#### **SECTION 9: PHYSICAL & CHEMICAL PROPERTIES**

APPEARANCE:	Cream/ Buff coloured foam: either foil, mineral glass, bitumen, gypsum, timber, magnesium silicate facings.
ODOUR:	Slight, non-offensive smell
pH:	Neutral
FLASH POINT:	Not Applicable
MELTING POINT:	Not Applicable
FREEZING POINT:	Not Applicable
PRODUCT DENSITY:	32kg/m <sup>3</sup>
SOLUBILITY IN WATER:	Not Soluble

#### **SECTION 10: STABILITY & REACTIVITY**

Product is stable and un-reactive under normal usage.

#### SECTION 11: TOXICOLOGICAL INFORMATION

Polyisocyanurate board is non-toxic and non-irritant.

#### **SECTION 12: ECOLOGICAL INFORMATION**

Product is inert and stable in water and soil.

#### **SECTION 13: DISPOSAL CONSIDERATIONS**

Waste is non- hazardous. Waste product and packaging should be disposed of in accordance with local laws and regulations.

#### **SECTION 14: TRANSPORT INFORMATION**

Read section 7 in conjunction with this section. Ensure load is secure before/during transit. Use mechanical lifting equipment when moving bulk quantities.



### **PRODUCT HEALTH & SAFETY**

#### **SECTION 15: REGULATORY INFORMATION**

Not Applicable

#### **SECTION 16: OTHER INFORMATION**

The information given in this sheet is based on our current knowledge of the product. It is given in good faith and refers only to those products named in this document. Unilin Insulation withhold the right to update and amend this document as necessary. The information should not be taken as a guarantee of performance. Users should conduct their own assessment and make applicable staff aware accordingly. For further assistance contact Unilin Technical Department.